

CLAIM SET AS AMENDED

1. (Currently Amended) A cleaning sheet which comprises a non-woven fabric having 10 to 90% by weight of thermoplastic fibers having a fiber length of 2 to 15 mm and a fineness of 10 to 150 dtex and 10 to 90% by weight of cellulosic fibers, ~~and has~~ said non-woven fabric having a number of tips of said thermoplastic fibers forming the non-woven fabric exposed on the surface of said cleaning sheet to have capability of scouring or scraping dirt off of a soiled surface, wherein said number of tips of said thermoplastic fibers is 20-4000/cm².

2. (Original) The cleaning sheet according to claim 1, which is impregnated with an aqueous detergent.

3. (Previously Presented) The cleaning sheet according to claim 1, wherein said sheet is an air-laid web comprising said thermoplastic fibers and said cellulosic fibers which have a fiber length of 0.1 to 15 mm, the fibers constituting said web being bonded by fusion or with a binder at their intersections.

4. (Original) The cleaning sheet according to claim 3, which comprises 30 to 90% by weight of said thermoplastic fibers and 10 to 70% by weight of said cellulosic fibers, and has a basis weight of 40 to 300 g/m².

5. (Original) The cleaning sheet according to claim 1, which comprises a sheet and at least one air-laid nonwoven fabric which is provided on at least one side of said sheet,

said sheet and said air-laid nonwoven fabric being laminated together into one body,

said sheet containing 30 to 100% by weight of said cellulosic fibers and having a basis weight of 30 to 200 g/m²,

said air-laid nonwoven fabric containing 30 to 100% by weight of said thermoplastic fibers and having a basis weight of 30 to 200 g/m² with a large number of the tips of said thermoplastic fibers being exposed on the surface of said air-laid nonwoven fabric.

6. (Original) The cleaning sheet according to claim 5, which is obtained by

forming an air-laid web comprising said cellulosic fibers that have a fiber length of 0.1 to 15 mm and bonding the fibers constituting said web at their intersections by fusion or with a binder to prepare said sheet,

separating forming an air-laid web comprising said thermoplastic fibers and bonding the fibers constituting said web at their intersections by fusion or with a binder to prepare said air-laid nonwoven fabric, and

bonding said air-laid nonwoven fabric to at least one side of said sheet.

7. (Original) The cleaning sheet according to claim 5, which is obtained by

superposing an air-laid web comprising said thermoplastic fibers on at least one side of an air-laid web comprising said cellulosic fibers that have a fiber length of 0.1 to 15 mm and

bonding the fibers constituting each of said webs among themselves at their intersections and also bonding said webs to each other by fusion or with a binder.

8. (Original) The cleaning sheet according to claim 1, which has been embossed.

9. (Original) The cleaning sheet according to claim 1, wherein said thermoplastic fibers comprise a low-melting resin and a high-melting resin, said low-melting resin forming at least a part of the fiber surface.

10. (Original) The cleaning sheet according to claim 1, wherein said thermoplastic fibers are crimped fibers.

11. (Original) The cleaning sheet according to claim 2, wherein said aqueous detergent contains an electrolyte.

12. (Original) A method of cleaning a soiled surface which comprises spraying the cleaning sheet according to claim 1 with an aqueous detergent and then rubbing the soiled surface with the sprayed cleaning sheet.

13. (Currently Amended) A cleaning sheet, comprising:
a non-woven fabric having 10 to 90% by weight of thermoplastic fibers, said thermoplastic fibers having a fiber length of 2 to 15 mm and a fineness of 10 to 150 dtex, ~~said thermoplastic fibers~~ said non-woven fabric having a number of tips of said thermoplastic fibers forming the non-woven fabric

exposed on the surface of said cleaning sheet in the range of 20 to 4000/cm²;
and

10 to 90% by weight of cellulosic fibers,

wherein said thermoplastic fibers are bonded at intersections thereof.

14. (Previously Presented) The cleaning sheet according to claim 1,
wherein the number of tips of said thermoplastic fibers is 50 to 2000/cm².

15. (Previously Presented) The cleaning sheet according to claim 1,
wherein the number of tips of said thermoplastic fibers is 100 to 1000/cm².